



**Laboratory for Chemical Production
in Electronic Industry**

Roztocka 145, Velke Prilepy 252 64, Czech Republic.

Tel.:420 608 508 824, Fax: 420 220 930 196, e-mail: marmot@marmot.cz, www.marmot.cz

Technical Data Sheet	MTR968
Product name:	MARMOT® Flux MTR968
Description and key properties:	
<ul style="list-style-type: none">• Non aggressive Electro-insulation Organic flux• Activated by unique MARMOT® patented combination of hydro-halide and inhibitor of corrosion• For hand and automated wetting soldering in electronics solder Sn60-63%Pb• For wave soldering after diluting• For soldering high-end electronics even highly oxidized color metals• Flux concentrate – dilute according to used process of soldering and solderability of soldered parts• The flux is not suitable for soldering by naked flame – it is highly flammable	
Operating manual: Flux is applied by foam, spray or wetting. Flux can be accordingly diluted to minimize residues after soldering	

Technical specification:	Corresponds to norm:	Classification:
	EN 29454-1	1.1.2.A
Fully complies EU directive - RoHS	DIN	F-SW-26
	J-STD	ROL1
Form	Liquid	
Aroma	Alcoholic	
Density	0,897	kg/dm ³
Melting point	-	C
Boiling point	82 - 84	C
Color	yellow - brownish	
Spread factor – USA methodology MIL-F-14256D	78-80	%
Spread areal – EU methodology	214	mm ²
Absolute corrosive effect on Cu mirror - EN 29455-5 (ISO 9455-5:1992)	Without depletion Cu 4000 Angstrom Without corrosion - Complies excellent	
- USA method MIL-F-14256D:	Without corrosion - Complies excellent	
corrosive effect tropical humidity 21 days	Without corrosion - Complies excellent	
Insulation resistance :		
1kV distance 1mm		M ohm
PCB distance 1 x 1mm	650	T ohm
electrical breakdown distance 1mm		KV
Soluble in:	Isopropyl alcohol	without limits
		g/lit.
Recommended thinner :	Isopropyl alcohol	
Recommended cleaner:	Isopropyl alcohol, Special water based washing bath	
Used methodology conform the norm MARMOT, M01-3 for led free solders M01.1		
Other proprieties: Solid substance read safety data sheet if released		
For aviation and military devices is recommend cleaning, for other usage we recommend to test the influence of flux residues on the device, according to the aspect of device and process of production. In all other application where the small residuum of the flux after soldering does not affect the product is not necessary to apply cleaning.		
Issued:	22.7.2008	
Revised	25.01.2013	

11.0.	Safety and health protection
11.1.	Long lasting and repeated contact with skin can cause irritation and sensibility, therefore is necessary to avoid direct contact. In case when it is not possible exclude possibility of direct skin contact, the workers must wear suitable personal protective equipment. Work area must be ventilated. Do not drink or eat during work. Do not use naked flame. After work, hands should be washed with soap and warm water and cared with protective cream.
11.2.	First Aid Inhalation – in case of excessive inhalation of flux fumes emitted during soldering, remove affected person to fresh air. Ingestion – in case of accidental Ingestion, wash out mouth with water and give enough pure water to drink. Skin contact – in case of skin contact, wash the place with soap and warm water. Eye contact – in case of eye contact, flush the eyes immediately with plenty of water. In case of large health damage or eyes contact, seek medical attention.
11.3.	Above mentioned precautions are recommended for health protection of the workers, obligatory measures are described in Safety Data Sheet (SDS) - if released, and do not substitute internal safety regulations of final customer.